

## Icelene LD224 Low Density Polyethylene Resin

**Applications:** 

Bakery Film, Compounding Foams, Blending resin

**Additive packages** 

Slip (750 ppm ), Antiblock (1000ppm) Antioxidant

## **PRODUCT DESCRIPTION**

LD224 is designed for blown and cast film applications with good balance of optical and mechanical properties for general purpose clarity packaging. LD224 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR.177.1520 ,covering safe use of polyolefins articles intended for direct food contact.

Properties*	Value (SI)	Value (English)	Method
Melt Index (190°C/2.16kg)	2.0 g/10 min	2.0 g/10 min	ASTM D1238
Density	0.924 g/cm <sup>3</sup>	0.924 g/cm <sup>3</sup>	ASTM D1505
Tensile strength at yield MD	1500 psi	10 MPa	ASTM D882
Tensile strength at yield TD	1600 psi	11 MPa	ASTM D882
Tensile strength at break MD	3600 psi	25 MPa	ASTM D882
Tensile strength at break TD	2700 psi	19 MPa	ASTM D882
Elongation MD	130%	130%	ASTM D882
Elongation TD	490%	490%	ASTM D882
1% Secant Modulus MD	30000 psi	210 MPa	ASTM D882
1% Secant Modulus TD	37000 psi	260 MPa	ASTM D882
Elmendorf Tear MD	440 g	440 g	ASTM D1922
Elmendorf Tear TD	110 g	110 g	ASTM D1922
Dart Drop Impact Strength (F <sub>50</sub> )	120 g	120 g	ASTM D1709A
Haze	6%	6%	ASTM D1003
Gloss (45°)	69	69	ASTM D2457

<sup>\*</sup> Typical Value of Properties which can vary with in specification limits and are not to be construed as specifications.

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, ICD America LLC disclaims responsibility for reliance and results of use of this information. ICD AMERICA LLC DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. ICD America LLC expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.

The above values were measured on a 1.5 mil (38.1  $\mu$ m) film produced on a 2.5 inch (63.5 mm) blown film line with a 2.5:1 BUR using a die gap of 30 mil (0.8mm) die gap.