

Icelene LD724 Low Density Polyethylene Resin

Applications:
Injection Molding

Additive packages
LD724 :Slip (None), Antiblock (None)

PRODUCT DESCRIPTION

ICELENE LD724 is certified prime resin for compounding and injection application.

Properties*	Test Method	Metric Units		English	
		Typical Value	Unit	Typical Value	Unit
Melt Flow Index ²	ASTM D1238	6.5	g/10 min.	6.5	g/10 min
Density (23°C)	ASTM D792	0.924	g/cm ³	0.924	g/cm ³
Tensile Modulus	ASTM D882	160	Mpa	23000	psi
Tensile Strength at Break	ASTM D882	150	%	150	%
Vicat Temperature	ASTM D1525	89	°C	192	°F

* Typical Value of Properties which can vary with in specification limits and are not to be construed as specifications.

² Condition 190°C/2.16 kg.

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, ICD America LLC disclaims responsibility for reliance and results of use of this information. ICD AMERICA LLC DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. ICD America LLC expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.