

## ICELENE PF-0118D Butene Copolymer LLDPE Film Resins

Grade	Additive packages	Applications	
ICELENE PF-0118D	Slip (1500 ppm), Antiblock (6300 ppm)	Trash bags, garment film, bags-on-roll	

## **PRODUCT DESCRIPTION**

ICELENE PF-0118D is a certified prime resin intended for use in trash bags, garment film, bags-on-roll. ICELENE PF-0118D Series resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without temperature or food-type restrictions, subject to technical suitability.

		Metric Units		English	
Properties*	Test Method	Typical Value	Unit	Typical Value	Unit
Melt Flow Index (2)	ASTM D1238	1.0	g/10 min.	1.0	g/10 min
Density (23°C)	ASTM D792	0.918	g/cm³	0.918	g/cm³
Film Properties <sup>1</sup>					
Thickness		25	μm	1.0	mil
Tear Strength					
MD	ASTM D1992	100	g	100	g
TD	ASTM D1992	330	g	330	g
Low Friction Puncture		34	J/mm	8	in-lb/mil
Dart Drop Impact Strength F50	ASTM D1709/A	100	g	100	g
Tensile Strengh					
MD	ASTM D882	49	Мра	7100	psi
TD	ASTM D882	34	Мра	4900	psi
Yield Strength					
MD	ASTM D882	11	MPa	1600	psi
TD	ASTM D882	11	MPa	1600	psi
Elongation					
MD	ASTM D882	540	%	540	%
TD	ASTM D882	830	%	830	%
1 % Secant Modulus		_			
MD	ASTM D882	200	MPa	29000	psi
TD	ASTM D882	230	MPa	33400	psi
Haze	ASTM D1003	11	%	11	%
Gloss @ 45º	ASTM 2457	56		56	

\* Typical Value of Properties which can vary with in specification limits and are not to be construed as specifications.

<sup>1</sup> Film properties are typical of blown film extruded on a 2.5" extruder with 4" die and 100-mil die gap at a blow up ratio of 2.5:1 but are dependent upon 2 Condition 190°C/2.16 kg.

2 Condition 190°C/2.16 kg. The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, ICD America LLC disclaims responsibility for reliance and results of use of this information. ICD AMERICA LLC DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. ICD America LLC expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.

> ICD America LLC 145 Huguenot Street, Suite 106, New Rochelle, NY 10801 Phone:914–633–4200 www.icdamerica.com