

# ICELENE HB5502C

## High Density Polyethylene

**PRODUCT DESCRIPTION**

ICELENE HB5502C is produced using licensors formulation for HHM 5502BN Blow Molding Hexene copolymer is designed for applications requiring excellent stiffness and stress crack resistance properties. intended for use as a general-purpose blow molding resin or sheet extrusion thermoforming resin. ICELENE HB5502C is cleared for use in articles or components of articles intended for contact with food under 21 CFR 177.1520(c) and meets the specifications in that paragraph.

Properties*	Test Method	Metric Units		English	
		Typical Value	Unit	Typical Value	Unit
Melt Flow Index <sup>(2)</sup>	ASTM D1238	0.35	g/10 min.	0.35	g/10 min
Density (23°C)	ASTM D1505	0.955	g/cc	0.955	g/cc
Enviromental Stress Crack Resistance (ESCR)					
Condition A, F <sub>50</sub> (100% Igepal)	ASTM D1693	45	h	45	h
Condition B, F <sub>50</sub>	ASTM D1693	35	h	35	h
Tensile Yield Strength,	ASTM D638				
2" (50 mm) per min.	Type IV	28	Mpa	4000	psi
Ultimate Elongation,	ASTM D638				
2" (50 mm) per min.	Type IV	>600	%	>600	%
Brittleness Temperature	ASTM D746	<-180	C	<-180	F
Flexural Modulus	ASTM D790	1378	MPa	200,000	psi.

\* Physical properties reported herein were determined on compression molded specimens prepared in accordance with Procedure C of ASTM D1928. The nominal properties reported herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, ICD America LLC disclaims responsibility for reliance and results of use of this information. ICD AMERICA LLC DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. ICD America LLC expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.

ICD America LLC  
145 Huguenot Street, Suite 106, New Rochelle, NY 10801  
Phone:914-633-4200  
www.icdamerica.com